

kim FLEX
FLEXIBLE FOAM SYSTEMS



kimpur

KIMTEKS POLYURETHANE

www.kimpur.com

kim FLEX

FLEXIBLE FOAM SYSTEMS

ECO FRIENDLY INTEGRAL SKIN SYSTEMS

Two-Component Foam Systems for the production of elastic integral skin foam parts for applications in the automotive and furniture industries.

Smooth Surface



Fast Curing

Good Flowability

Flexibility

Eco-Friendly



kim FLEX

ESNEK KÖPÜK SİSTEMLERİ

KIMflex FI 032 - Izokim FI 002

KimFLEX FI	COMPONENTS		KIMflex FI 032 Izokim FI 002
	REACTION PROFILE	UNIT	VALUE
Mixing Ratio (polymix / iso)	By weight	100/48 ± 2	KİMPUR Internal Method
Stirring Time	S	5	KİMPUR Internal Method
Cream Time	S	48 ± 2	KİMPUR Internal Method
Gell Time	S	39 ± 4	KİMPUR Internal Method
Tack - Free Time	S	49 ± 4	KİMPUR Internal Method
Rise Time	S	58 ± 4	KİMPUR Internal Method
Demoulding Time	S	180	KİMPUR Internal Method
Free Rise Density	kg/m ³	210 ± 10	KİMPUR Internal Method
Moulded Density	kg/m ³	360	DIN ISO 7619-1
Hardness	shA	60	ISO 845

Data refer to laboratory tests made with components at 23°C, hand-mixed with mechanical stirrer at 5000 rpm.

Reported values may vary depending on processing condition.



kimpur

KİMTEKS POLYURETHANE



TURKEY'S POLYURETHANE SYSTEM HOUSE

36
Years
Experience

1000
TİM TÜRKİYE İHRACATÇI VE İHRACATÇI FİRMASI
2018 TÜRKİYE'NİN İLK 1000 İHRACATÇI FİRMASI
TOP 1000 EXPORTERS OF TURKEY

Turkey's top
500
industrial enterprises

PRODUCTION CAPACITY
110.000
TONS

KİMTEKS POLİÜRETAN SANAYİ VE TİCARET A.Ş.

HEAD OFFICE:

Emniyet Evleri Mah. Eski Büyükdere
Cad. Sapphire Plz. No: 1/4 Kat: 19 D: 01
Kağıthane 34415 İstanbul TÜRKİYE
Tel: +90 212 809 15 50
Fax: +90 212 809 15 49

GEBZE FACTORY:

Gebze Plastikçiler Organize
Sanayi Bölgesi 7. Cadde No: 43
41400 Gebze Kocaeli TÜRKİYE
Tel: +90 262 751 44 71
Fax: +90 262 751 02 57

GAZİANTEP BRANCH:

Çakmak Mahallesi Haraf Sokak
No: 10A Şehitkamil Gaziantep
TÜRKİYE
Tel: +90 342 325 57 97
Fax: +90 342 325 57 97

www.kimpur.com